



MANNER **PLASTICS, L.P.**

500 Interchange Street, McKinney, Texas 75071

Phone 972-542-6789

FAX 972-540-0086

Product Data Sheet

MANNER M1581

Flexible PVC

Recommended Applications:

Lead-free general purpose injection molding compound. Manner M1581 is UL recognized under QMFZ2 and QMFZ8. This product complies with the European Union Restriction on Hazardous Substances directive.

PROPERTY

Hardness Shore Durometer (± 3)
Instantaneous

Specific Gravity (± .02)

Unaged Dumbbells: 30 mil

Tensile Strength, avg. PSI
100% Modulus avg. PSI

VALUE

C81

1.45

1854

1665

ASTM Test Method

D-2240

D-792

D-638

D-638